

Anterior and posterior light cured restorative

Nexcomp is Nano Hybrid Composite Resin for Anterior and Posterior Resorations, Nexcomp is reinforced nanofiller composite Nexcomp is the ideal nanofilled microhybrid to use both anteriorly and posteriorly. Leading clinicians agree that this versatile material is in a class by itself

INDICATION

Hybrid Composite Resin

Nano

- Class I, II, III, IV, V restorations
- Core-buildup to replace missing tooth
- Diastema closures
- Direct veneers
- Composite and porcelain repairs

CONTRAINDICATIONS

Nexcomp should not be used if patients are known to be allergic to methacrylate

INSTRUCTIONS

- Select the desired type and shade of Nexcomp composite prior to isolating and preparing
 Clean the preparation with a slurry of purice and water, Rinse and dry the preparation
 Apply 37% Meta Etchant gel to available ename! / dentin for 15 seconds, Remove gel and rinse for 20 seconds, Blot dry keep moist, do not rub.
 Apply Bond to the tooth-Apply a double coal of Meta P&Bond by using microbrush.
- double coat of Meta P&Bond by using microbrush.
 Gently air dry for 5 seconds, Light cure for 10 seconds, If you apply other product to saturate all internal surfaces, or bonding agent according to manufacturer's instructions

 Bace composite-Place Nexcomp in increments of 2mm or less in Anterior and posterior, restructions
- and posterior restorations.
 Cure for 20 seconds in increments of

META[®] BIOMED

Finish and Polish-After contouring composite, polish surface with finishing and polishing proximal areas, Occlusion-Check lateral and centric occlusion. Adjust as nessary.

SIDE EFFECTS

None known to date

CAUTIONS

- Avoid contact of Nexcomp with the skin/mucous membrane or eyes
- None polymerized Nexcomp may be causes lightly, reversible irrilation or lead to a general sensitization against methacrylates.
- Keep away from child.
- For dental use only
- Do not use after the date of expiration.
- Exposure to light may be lead to premature polymerization

STORAGE

- Storage 18~24°C(64~75°F)
- Close syringe cap immediately after use.
- Avoid from directly sun light.

SHELF LIFE

2 years from the manufacturing date

COMPONENTS

- Nexcomp Set
- 4g x 7 Syringe (A1, A2, A3, A3.5, B2, A2E, B2E)

- Nexcomp Kit

- 4g x 7 Syringe (A1, A2, A3, A3,5, B2, A2E, B2E)
 Meta P&Bond 5g
 Meta Etchant 3g
- Nexcomp Refill
- 4g x 1 Syringe (A1B, A2B, A3B, A3.5B, B2B, A2E, B2E, A1,
 A2, A3, A3.5, A4, B1, B2, B3, C2, C3, D2,
 D3, TL, WT, OP, OA2, OA3)

SYMBOLS



LOT Batch Code

CE-Mark and identification number of notified body.
Product conforms to the essential requirements
of the Medical Device Directive 93/42/EEC

INSTRUCTION FOR USE

Attention, See instruction for use Manufacturer

META BIOMED COLLTD.

Made in Korea

Manufactured by METABIOMED COLTD.

AM 634, Yeonje-ri, Gang-oe-myeon, Cheong-won-gun Chungcheongbuk-do, Korea Tel:+82-43-216-0433 Fax:+82-43-217-1988 E-mail: into@meta-biomed.com Web site: http://www.meta-biomed.com

DM-40-6

CHECKING SHEET

Nexcomp

TITLE	
CODE	DM-40-6
SIZE	207x174mm
PAPER	60g 모조
MAIN COLOR	INDIGO 2767C 별색 단도
SPECIAL	
FUNCTION	
PRINT COLOR	



CONFIRMATION	META BIOMED CO.LTD.
RECOGNITION	김상일
DESIGNER	진희남
DATE	2009. 07. 10.

SIGN

2011, 06, 02 → DM-40-6 / 주소변경 (홍선미)